

from 300-mesh upwards, although these are too fragile for some work. The Institute of Mining and Metallurgy (I.M.M.)<sup>(4)</sup> screens are more robust, with the thickness of the wire approximately equal to the size of the apertures. The Tyler series, which is standard in the United States, is intermediate between the two British series. Details of the three series of screens<sup>(3)</sup> are given in Table 1.1, together with the American Society for Testing Materials (ASTM) series<sup>(5)</sup>.

Table 1.1. Standard sieve sizes

British fine mesh (B.S.S. 410) <sup>(3)</sup>			I.M.M. <sup>(4)</sup>			U.S. Tyler <sup>(5)</sup>			U.S. A.S.T.M. <sup>(5)</sup>		
Sieve no.	Nominal aperture		Sieve no.	Nominal aperture		Sieve no.	Nominal aperture		Sieve no.	Nominal aperture	
	in.	μm		in.	μm		in.	μm		in.	μm
						325	0.0017	43	325	0.0017	44
						270	0.0021	53	270	0.0021	53
300	0.0021	53				250	0.0024	61	230	0.0024	61
240	0.0026	66	200	0.0025	63	200	0.0029	74	200	0.0029	74
200	0.0030	76							170	0.0034	88
170	0.0035	89	150	0.0033	84	170	0.0035	89			
150	0.0041	104				150	0.0041	104	140	0.0041	104
120	0.0049	124	120	0.0042	107	115	0.0049	125	120	0.0049	125
100	0.0060	152	100	0.0050	127	100	0.0058	147	100	0.0059	150
			90	0.0055	139	80	0.0069	175	80	0.0070	177
85	0.0070	178	80	0.0062	157	65	0.0082	208	70	0.0083	210
			70	0.0071	180				60	0.0098	250
72	0.0083	211	60	0.0083	211	60	0.0097	246	50	0.0117	297
60	0.0099	251							45	0.0138	350
52	0.0116	295	50	0.0100	254	48	0.0116	295	40	0.0165	420
			40	0.0125	347	42	0.0133	351	35	0.0197	500
44	0.0139	353				35	0.0164	417	30	0.0232	590
36	0.0166	422	30	0.0166	422	32	0.0195	495			
30	0.0197	500				28	0.0232	589			
25	0.0236	600									
22	0.0275	699	20	0.0250	635	24	0.0276	701	25	0.0280	710
18	0.0336	853	16	0.0312	792	20	0.0328	833	20	0.0331	840
16	0.0395	1003				16	0.0390	991	18	0.0394	1000
14	0.0474	1204	12	0.0416	1056	14	0.0460	1168	16	0.0469	1190
12	0.0553	1405	10	0.0500	1270	12	0.0550	1397			
10	0.0660	1676	8	0.0620	1574	10	0.0650	1651	14	0.0555	1410
8	0.0810	2057				9	0.0780	1981	12	0.0661	1680
7	0.0949	2411				8	0.0930	2362	10	0.0787	2000
6	0.1107	2812	5	0.1000	2540	7	0.1100	2794	8	0.0937	2380
5	0.1320	3353				6	0.1310	3327			
						5	0.1560	3962	7	0.1110	2839
						4	0.1850	4699			
									6	0.1320	3360
									5	0.1570	4000
									4	0.1870	4760

The efficiency of screening is defined as the ratio of the mass of material which passes the screen to that which is capable of passing. This will differ according to the size of the material. It may be assumed that the rate of passage of particles of a given size through the screen is proportional to the number or mass of particles of that size on the screen at any